This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problem Mailbox.

Priority Japanese Application JP 11-337702

整理番号=A087290

平成11年11月29日 頁: 8/ 9

【表1】

			実施例	1	比較例							
	1	2	3	1	2 .	3	4	5	6			
基材層	1		10	30	0	3	40	50	0	100		
	PET樹脂	95	90	70	100	95	60	50	100	0		
両面層 PC樹脂		100	100	100	100	100	100	100				
全光透流	89	88.9	88.1	90	90	88.5	88.8	90	90.6			
暴度(%)		2.2	2.6	6.1	1	1.2	15	22	1	1		
デュポン街	撃強度(J)	1.96	1.91	2.18	1.96	1.95	2.15	2.16	1.84	2.4		

[0026]

【表2】

			実施例)	上 較例						
		1	2	3	1	2	3	4	5	6	
2次成	2次成形性		0	0	0	0	Δ	Δ	0	×	
耐熱性	90℃	0	0	0	0	0	0	0	×	O	
	100℃	0	0	0	0	0	0	0	×	0	
Ĺ	110℃	0	0	0	Δ	. Δ	0	0	×	0	

[0027]

【表3】

		実	拖 例	比較例					
		4	_ 5	5	6	7	8		
構成比	表面層(重量%)	5	15	0	0	2.5	20		
	基材層(重量%)	90	70	100	. 0	95	.60		
	表面層(重量%)	5	15	0	100	2.5	20		
	2次成形性	0	0	0	×	0	×		
耐熱性	90℃	0	0	×	0	0	0		
	100℃	0	0	×	Ο	0	0		
	110℃	0	0	×	0	×	0		

[0028]

【発明の効果】

基材層がポリエチレンテレフタレート系樹脂とポリカーボネート系樹脂からなり

、表面層がポリカーボネート系樹脂からなる電子部品包装容器は強度、耐熱性、

成形性、透明性、曇度に優れキャリアテープに好適に用いることが出来る。



_	_	٦
7	_	ł
	_	
	a	٦.
ſ	_	1
	۲	1
•	a	d
	E	-
-	_	

			Framoles			Comp	arative	Comparative Examples	les	
			- Amore				-		-	,
	•	-	2	٣		7	3	4	2	٥
						·		0	c	100
	חל בפי הם	Ŋ	10	30	0	~	4 O	DC.	>	201
Base Layer						L	(ď	100	_
	pro resin	95	90	70	100	95	00	000	TOOT	
							,	,	•	
		100	100	100	100	100	100	700	-	
Both surtace layers FC	FC LESTII									,
	(0.)	00	σαα	28	90	90	88.5	88.8	90	90.6
moral light transmittance (*)	tance (6)	0	200							,
		,	2 6 7	7	_	1.2	15	22	-	
(%) significations (%)		7.7	7.0	1.0	1					
		,	,	70	1 96	1 95	2,15	1 0 1 0 1 0 1 0 1 0 1 0 1 0 1 0 1 0 1 0	1.84	2.4
In, pont impact strength	ngth (J)	1.96	1.71	6.10	7:30	2				
חת דמונה דייינים										

[Table 2]

		1	_	- [- 1					
		9		×	(o	(0	(0	
les		5		0		×		×		×	
Examp		4		◁		0		0		0	
Comparative Examples	<u></u>	3		◁		0		0		0	
Comp		7		0		0		0		◁	
	,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,	⊣		0		0		0		◁	
		m		С)	С)	С)	0)
Evamples	ישלווושעי	2		С		. C)	C)	. C)
	4	-	1	C)	C)	C)	·C)
						2000	ייייייייייייייייייייייייייייייייייייייי	1000	つ OOT	11000	ノロエー
					Post-formability		Heat resistance				